

DAVID J HEFFER AND ASSOCIATES

Consulting Textile
Technologists

22 Hicks Street, Lara, Vic, 3212
Tel: (03) 5282 1337

djheffer@djha.com.au
www.djha.com.au

ABN. 87 710 470 062



LABORATORY REPORT

Date : 13 June 2023

Report Number: 237906

Client: CHARLES PARSONS INTERIORS
191-193 CLEVELAND STREET
REDFERN NSW 2016

Reference: Christina McFarlane

Sample: woven, Montego, 100% polyester, 120gsm

Results:

Flammability (AS1530-1993 Part 2)

Direction	Speed factor (S)	Heat factor (H)	Spread factor (E)	Flammability Index
warp	-	1	3	4
weft	-	0	3	

Note: The heat factor (H) will range from 0 upwards, the speed factor (S) from 0 to 60 and the spread factor (E) from 0 to 40. The value of the flammability index (I) will range from 0 to 100 for most materials.

DAVID J HEFFER
DIRECTOR