

# DAVID J HEFFER AND ASSOCIATES

Consulting Textile  
Technologists

22 Hicks Street, Lara, Vic, 3212  
Tel: (03) 5282 1337

djheffer@djha.com.au  
www.djha.com.au

ABN. 87 710 470 062



## LABORATORY REPORT

Date : 5 September 2024

Report Number: 248588

Client: CHARLES PARSONS (NZ) LTD  
HARBOURSIDE BUSINESS PARK  
525 ROSEBANK ROAD  
AVONDALE NEW ZEALAND 1140

Reference: Tina Grant

Sample: woven chenille, Vintage, 100% polyester, 440gsm

### Results:

Flammability (AS1530-1993 Part 2)

Direction	Speed factor (S)	Heat factor (H)	Spread factor (E)	Flammability index
warp	-	1	1	2
weft	-	0	0	

Note: The heat factor (H) will range from 0 upwards, the speed factor (S) from 0 to 60 and the spread factor (E) from 0 to 40. The value of the flammability index (I) will range from 0 to 100 for most materials.

DAVID J HEFFER  
DIRECTOR